

VICTORIA Balance „Exclusive”

Parameter	Unit	Value	Comments
Size		A4	
Grammage	g/m ²	80 ± 2	Computerized measurement and adjustment. Calibration of measuring heads and parameter control according to PN-ISO 536:1996
Moisture	%	3,8-5,0	Computerized measurement and adjustment. Calibration of measuring heads and parameter control according to PN-ISO 287:1994
Thickness	µm	108 ± 3	PN-EN ISO 534:2005
Whiteness CIE		166 ± 2	PN-ISO 11475:2002 Top and bottom avg
Opacity	%	≥94	ISO 2471:1998
Air Permeability	cm ³ /min	≤1.250	PN-P-50176-3:1994
Smoothness	cm ³ /min	160±50	PN-93/P-50166.02 Top and bottom avg

Conditioning at: RH 50 ± 2 % temp. 23± 1°C PN-EN-20187 :2000
 ISO 9001 – Quality control, ISO 14001 – Environmental protection, ISO 9706 – Permanent paper
 OHSAS 18001 – Health and Safety